Nickel Alloy X

Alloy X · UNS N06002

Oxidation-resistant nickel alloy powder for combustion, furnace, hot-gas, and high-temperature hardware.

Designations: Alloy X · UNS N06002 · GH3536

Supply

Item	Value
Particle-size cuts	15–45 µm · 15–53 µm · 45–106 µm
Processes	LPBF
Minimum pack	1 kg (paid samples)
Packaging	Aluminium-foil bag · 1 kg sealed pack · Drum
Documents	Lot-specific COA · Particle-size report · Safety data sheet · Chemistry report
List price	US$51–100/kg, EXW China

Our list price for LPBF cuts (15–45 µm or 15–53 µm), per kg, EXW China, from 1 kg. It is set at 80–90% of the public list prices of mainstream suppliers checked in October 2026. Other particle-size cuts are priced by agreement; packing and freight are quoted separately. Your written quotation from our official corporate email confirms the price, lead time and terms for your quantity, particle size and documents.

Chemical composition, wt.%

Element	Limit
Ni	Balance
Cr	20.5–23.0
Fe	17.0–20.0
Mo	8.0–10.0
Co	0.5–2.5
W	0.2–1.0
C	0.05–0.15
Si	≤1.0
Mn	≤1.0
Al	≤0.5
O	≤0.02
N	≤0.02

Typical partner-plant datasheet limits for Alloy X-type (GH3536) powder, wt.%. The quoted lot COA governs.

Powder properties · LPBF screening window

Property	Value	Note
D10	≥15 μm	
D50	30–40 μm	
D90	≤60 μm	
Sphericity	≥0.90	Method to be confirmed
Apparent density	≥4.4 g/cm³	
Tap density	≥5.0 g/cm³	
Flow	≤18 s/50 g	Method and conditioning to be confirmed

An Alloy X screening basis; build cracking and thermal exposure remain process-level risks.

Typical mechanical properties

Condition	Temperature	Tensile	Yield	Elongation	Note
Heat treated	Room temperature	≥700 MPa	≥300 MPa	≥30%	
Heat treated	900 °C	≥220 MPa	≥170 MPa	≥20%	

Partner-plant datasheet values for LPBF test bars at room temperature unless stated. Printed-part properties depend on machine, parameters, orientation, and post-processing.

Typical values, not a lot certificate. The certificate of analysis for the quoted lot governs. Formal quotations and commercial terms are valid only when issued from our official corporate email.

Request a quote: https://metal3dpowder.com/rfq/?product=hastelloyx · Grade page: https://metal3dpowder.com/products/hastelloyx/
Suzhou Como Precision Materials Co., Ltd. (SZCOMO) · info@szcomo.com · Exporting metal powders since 2016 · Issued 2026-10-26