Pure Copper

Cu ≥99.8%

High-conductivity pure copper powder for induction coils, heat exchangers, cold plates, and electrical parts.

Designations: Pure copper · Cu · Oxygen-controlled copper powder

Supply

Item	Value
Particle-size cuts	15–45 µm · 15–53 µm
Processes	LPBF
Minimum pack	1 kg (paid samples)
Packaging	Aluminium-foil bag · 1 kg sealed pack · Drum
Documents	Lot-specific COA · Particle-size report · Safety data sheet · Chemistry report
List price	US$45–79/kg, EXW China

Our list price for LPBF cuts (15–45 µm or 15–53 µm), per kg, EXW China, from 1 kg. It is set at 80–90% of the public list prices of mainstream suppliers checked in October 2026. Other particle-size cuts are priced by agreement; packing and freight are quoted separately. Your written quotation from our official corporate email confirms the price, lead time and terms for your quantity, particle size and documents.

Chemical composition, wt.%

Element	Limit
Cu	Balance
O	≤0.05
Fe	≤0.005
S	≤0.005
Pb	≤0.005
Sb	≤0.002
Others	≤0.1

Typical partner-plant datasheet limits, wt.%. The quoted lot COA governs.

Powder properties · LPBF screening window

Property	Value	Note
D10	≥10 µm	
D50	25–35 µm	
D90	≤60 µm	
Sphericity	≈0.90	Method to be confirmed
Apparent density	≥5.0 g/cm³	
Tap density	≥5.2 g/cm³	
Flow	≤22 s/50 g	Method and conditioning to be confirmed

A partner-plant datasheet screening basis for this grade; the delivered lot COA remains controlling.

Typical mechanical properties

Condition	Temperature	Tensile	Yield	Elongation	Note
As built	Room temperature	≥240 MPa	≥165 MPa	≥30%	

Partner-plant datasheet values for LPBF test bars at room temperature unless stated. Printed-part properties depend on machine, parameters, orientation, and post-processing.

Example low-oxygen lot from a second partner

Item	Value
Oxygen	60 ppm
Copper	≥99.95%
D10 / D50 / D90	12.11 / 33.5 / 57.97 µm
Apparent density	5.00 g/cm³
Tap density	5.88 g/cm³
Flow	20 s/50 g

Values from one lot test report of vacuum induction gas atomized copper powder. The same partner's standard limit for copper powder is ≤500 ppm oxygen; every quoted lot is reported on its own COA.

Typical values, not a lot certificate. The certificate of analysis for the quoted lot governs. Formal quotations and commercial terms are valid only when issued from our official corporate email.

Request a quote: https://metal3dpowder.com/rfq/?product=pure-copper · Grade page: https://metal3dpowder.com/products/pure-copper/

Suzhou Como Precision Materials Co., Ltd. (SZCOMO) · info@szcomo.com · Exporting metal powders since 2016 · Issued 2026-10-26